AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 **Test Number** : 20-006537

Issue Date : 17/02/2021 Print Date : 17/02/2021

6701253933

Order Number:

Sample Description Clients Ref : "Obex Grid Cut X"

Entrance Matting

Colour : Black and Grey End Use : Entryway mat

Nominal Composition: 100% Nylon with PVC backing

ISO 9239.1:2010 Part 1 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 15-12-2020

Date Tested 17-02-2021

CHF Value 2 3 Mean 1 5.4 5.9 5.7 5.7 kW/m² Length 8.4 kW/m² Width Smoke Value 2 3 1 Mean 667 621 656 679 Length %.min 535 Width %.min

Melting Yes

228720 48816 Page 1 of 2

 Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.





MICHAEL A. JACKSON B.Sc.(Hons)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 **Test Number** : 20-006537

Issue Date : 17/02/2021
Print Date : 17/02/2021
Order Number : 6701253933

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

Results in accordance with section 9.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

228720 48816 Page 2 of 2

 Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.





MICHAEL A. JACKSON B.Sc.(Hons)