

Valores acústicos

EDGE LIT



Absorción del sonido (ISO 354)


Impacto del sonido (ISO 140-8 / ISO 10140-3)

Edge Lit PVC-Free WellBAC™
Comfort Cushion α_w 0.25 Clase E

Edge Lit PVC-Free WellBAC™
Comfort Cushion ΔL_w 30dB

Coefficiente de absorción del sonido Alpha α_s

Frecuencia (Hz)	PVC-Free WellBAC™ Comfort Cushion α_s
100	0.02
125	0.02
160	0.00
200	0.02
250	0.07
315	0.09
400	0.16
500	0.22
630	0.32
800	0.34
1000	0.26
1250	0.21
1600	0.21
2000	0.22
2500	0.25
3150	0.31
4000	0.35
5000	0.40



α_p Valores (Edge Lit PVC-Free WellBAC™ Comfort Cushion)					
125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz
0.00	0.05	0.25	0.25	0.25	0.35

α_w	Clase
(valor global) 0.25	E