ACCS
AUSTRALIAN CARPET CLASSIFICATION SCHEME



Registration Certificate

Carpet Name:	*CONSEQUENCE 2.0 - SEQUEL*
Licensee:	*MILLIKEN (AUSTRALIA) PTY LTD*
Licence Number:	*008*
Label Number:	*14151*
ACCS Contract Grading:	*CEHD 4**
ACCS Residential Grading:	*NONE*
Suitable for Stairs:	*Yes*
Date Printed:	*14/09/2016*



Allan Firth

Allan Firth
Secretary ACCS

CARPET
IT JUST FEELS BETTER

AUSTRALIAN CARPET MARK

Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303
PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560
Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details: **Company: MILLIKEN (AUSTRALIA) PTY LTD** **Label No: 14151**

Licence No: 008 **Office No: 5972**

Names:

CONSEQUENCE 2.0 - SEQUEL

Details:

Awarded Res Grade:	NONE	
Awarded Con Grade:	CEHD	4*
Registered On:		24/07/2014
Active:		Yes
Date In-Active:		
Manufacture Method:		Tufted
Twist Set:		N/A
Dyeing Method:		Melt Dyed
#Colours/Designs:		20
Backing Type:		Foam
Felted:		N/A
Spinning System:		BCF
Insect Resist Agent:		N/A
Filament:		/
Master Product:		

Hexapod Scores:

	Texture	WA	Colour	WA	Thickness (mm)	(%)
1500:	4.5	4.0	4.5	4.5	0.3	7.5
8000:	3.5	3.5	4.0	4.0	0.8	20.0

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	16	16	16
Volume Density:	20	20	20
Tuft Density:	9	9	9
Dyn Load:	5	5	5
Stat Load:	4	4	5
Soiling Prop:	14	14	16
Abrasion Res:	10	10	10
Sub Total:	78	78	81
Panel Assess:	14	14	19
Total:	92	92	100

Calc Residential Grade: REHD2 6*

Calc Contract Grade: CHD 3*

Test Results:

Pile Mass g/m² (oz/yd²):	915	(27.0)
SPM g/m² (oz/yd²):	597	(17.6)
Stated Pile Height (mm):		3.1
Minimum Pile Height (mm):		0.0
Maximum Pile Height (mm):		0.0
Dynamic Loading Loss (%):		15.0
Static Loading Loss (%):		20.0
Tex (g/1000m):		469
Measured Pile Thickness (mm):		4.0
Machine Gauge (Tufts/dm):		39.4
Meas Tufts Perp to Selvedge:		39.9
Meas Tufts Para to Selvedge:		48.0
Treated For Soiling Resistance:		Yes
Soil Resist Inhibitor:		Yes
Stain Resist Inhibitor:		Yes

Quality Assurance Test:

Cut Pile (%):	0
Loop Pile (%):	100
Panel Assessment Contract:	14
Panel Assessment Residential:	14
Suitable For Stairs:	Yes

Tile: Yes SheetGoods: No

Fibre Signature: NBA:100

Calculations

Pile Height(mm):		3.4
Tuft Density(per dm²):		1915.2
GSPM(g/m²):		415.0
GSPM (abrasive) (g/m²):		275.0
Soiling Propensity:	12.0	+2.0

OAF Values

OAF: 4.2

Calc Density (+-5%):0.14 0.149 0.16

Base Fibre: NYLON

Benchmarks:

RHD1	0	RHD2	3.5
REHD1	3.5	REHD2	3.5

Environmental Classification:

ECS:

Level: 0

	Calc	B/M	P/F
Acoustic:	4	3	PASS
Thermal:	26.8	15	PASS
VOC:			
TVOC	10		

Notes:

23/7/14 Submitted by T Nguyen. 30/7/14 Panel awarded CEHD(S) 4*. 24/3/15 Deactivated and name CONSEQUENCE 2.0 - SEQUEL removed. 9/5/16 Now under Milliken. 14/9/16 Reactivated as inactivated by Licensee in error.