

Valores acústicos

PER CONTRA / In Contrast / On The Contrary



Absorción del sonido (ISO 354)


Impacto del sonido (ISO 140-8 / ISO 10140-3)

Per Contra Almohadillado α_w 0.30 (H) Clase D

Per Contra Almohadillado ΔL_w 34dB

Coefficiente de absorción del sonido Alpha α_s

Frecuencia (Hz)	Almohadillado α_s
100	0.03
125	0.02
160	0.03
200	0.05
250	0.08
315	0.18
400	0.52
500	0.42
630	0.27
800	0.24
1000	0.26
1250	0.27
1600	0.29
2000	0.33
2500	0.33
3150	0.40
4000	0.42
5000	0.48



α_p Valores (Almohadillado)					
125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz
0.00	0.10	0.40	0.25	0.30	0.45

α_w	Clase
(valor global)	
0.30 (H)	D