

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client : Milliken (Aus 171 Briens F Northmead I			lssue Print		20-00261 24/06/202 24/06/202 67012075	20 20		
Sample Description	Tufted loop pile carpet plank- End Use : Flooring Nominal Composition : 10 Nominal Mass per Unit Area/E	0% Nylon	•					
O 9239.1:2010 Part 1	Reaction to Fire Tests for Flo Radiant Heat Source	oorings. Determinatio		-	our using a			
	Date of Sample Arrival25/05/2020Date Tested23/06/2020							
	CHF Value Length	1 7.8	2 7.4	3 7.4	Mean 7.5	kW/m²		
	Width	8.0	-	-	-	kW/m²		
	Smoke Value	1	2	3	Mean			
	Length	162	185	173	173	%.min		
	Width	93	-	-	-	%.min		
	Melting				Yes			

206715

44413

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No. 983

985

1356

Page 1 of 2

AWTA LIMITED



APPROVED SIGNATORY

12

0204/11/06

(C)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client :	Milliken (Australia) Pty Ltd	Test Number	:	20-002619
	171 Briens Road	Issue Date	:	24/06/2020
	Northmead NSW 2152	Print Date	:	24/06/2020
			r:	6701207506

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 9.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

206715

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

44413



the Managing Director of AWTA Ltd

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No.

983 985

1356

Page 2 of 2





C