AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 **Test Number** : 20-004267

Issue Date : 24/09/2020 Print Date : 24/09/2020

6701226415

Order Number:

Sample Description Clients Ref : "Quattra Base"

Loop pile tufted carpet on WELLBAC Comfort Backing

Colour: Multicolour/Multidesign Nominal Composition: 100% Nylon

Nominal Mass per Unit Area/Density: Approx 11.5kg/m2

Nominal Thickness: Approx 8mm

AS ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 24/08/2020 **Date Tested** 24/09/2020 **CHF Value** 2 3 1 Mean Length 8.7 kW/m² Width kW/m² 6 1 6.9 59 6.3 Smoke Value 2 1 3 Mean Length 105 %.min Width 122 117 168 136 %.min

Melting Yes

215739 46162 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

AWTA LIMITED

MICHAEL A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 **Test Number** : 20-004267

 Issue Date
 : 24/09/2020

 Print Date
 : 24/09/2020

 Order Number : 6701226415

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

215739 46162

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved Page 2 of 2



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Machin

MICHAEL A. JACKSON B.Sc.(Hons)

0204/11/06

APPROVED SIGNATORY