

AMPLIFIER (OCTAVE / TREBLE)

Sample description as provided by customer

Pile weight mass/unit area **425 g/m²**

Construction Details **Tufted Secondary Backing B2 HARD BACKING**

Style **Loop Pile**

The Samples Tested Were Modular Carpet **500 mm X 500 mm**

Order No. **PO 6700573886**

Pile Fibre Content **100% SOLUTION DYED NYLON**

Colour **Grey/Charcoal**

Pile Height **mm**

TEST METHOD: ISO 9239-1(2010 06-15) Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the New Zealand Building Code Clause C2.1 (January 2017). Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date **Nov 2017**

Test Date **15 Nov 2017**

Total Thickness **mm**

Assembly System: DIRECT STICK (Details Below).

The floor covering was directly stuck to the substrate using **Water Based Surface Contact adhesive**.

Substrate: Non-Combustible - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring. The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests: **Length** Direction Critical Radiant Flux **4.2 kW/m²**
Width Direction Critical Radiant Flux **3.8 kW/m²**

Specimen Tests conducted in the Width Direction				
	Specimen #1	Specimen #2	Specimen #3	Mean
Critical Radiant Flux (kW/m ²)	3.8	4.1	4.3	4.1

The value quoted below is as required by the New Zealand Building Code Clause C2.1 (January 2017) "Minimum critical radiant flux when tested to ISO 9239-1:2010". Hence the Radiant Flux quoted is the value at Flame-Out/Extinguishment Not after a 30 minute burn as used in Europe.

Mean Critical Radiant Flux **4.1** kW/m²

Observations: **The samples shrunk away from the heat source, ignited and burnt a relatively short distance.**

ISO 9239-1:2010 Clause 10(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCNZ is given on this test report page.



M. B. Webb
Technical Manager

DATE: 15 Nov 2017

Performance & Approvals
Accreditation No. 15393
Accredited for compliance with ISO/IEC 17025.

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	195	196	265	363	471	670	845	1127	1503	1912	/							
2	197	198	268	325	427	744	997	1191	1597	2005	/							
3	198	199	248	309	468	691	988	1125	1619									

TESTS

BURNING CHARACTERISTICS

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)
Initial Test: Length	450	2,095
Specimen Tests: Width		
1	480	2,278
2	460	2,032
3	442	1,892
Mean	461	2,067




M. B. Webb
 Technical Manager

DATE: 15 Nov 2017

Performance and Approvals
 Accreditation No. 15393
 Accredited for compliance
 with ISO/IEC 17025.

2004 04 09 21341 15 November 2017