

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Milliken (Australia) Pty Ltd  
171 Briens Road  
Northmead NSW 2152

**Test Number :** 20-000260  
**Issue Date :** 3/03/2020  
**Print Date :** 3/03/2020  
**Order Number :** 6701177888

**Sample Description** Clients Ref : "Pip Base" (Multi-Colour/Multi-Design)  
Multi Level Tufted Loop Backing: WellBAC Comfort Plus Cushion  
Nominal Composition : 100% Nylon  
Nominal Mass per Unit Area/Density : Approx: 3493g/m2  
Nominal Thickness : Approx: 8mm

### AS/ISO 9239.1-2003

#### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 21/01/2020

Date Tested 02/03/2020

CHF Value	1	2	3	Mean
Length	10.2	10.6	8.7	9.8 kW/m <sup>2</sup>
Width	10.2	-	-	- kW/m <sup>2</sup>

Smoke Value	1	2	3	Mean
Length	154	110	165	143 %min
Width	118	-	-	- %min

Melting Yes

196083

41882

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing : Accreditation No. 983  
- Mechanical Testing : Accreditation No. 985  
- Performance & Approvals Testing : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Milliken (Australia) Pty Ltd  
171 Briens Road  
Northmead NSW 2152

**Test Number :** 20-000260  
**Issue Date :** 3/03/2020  
**Print Date :** 3/03/2020  
**Order Number :** 6701177888

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23\pm 2^{\circ}\text{C}$  and relative humidity of  $50\pm 5\%$  for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

196083

41882

Page 2 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR