

Milliken® Daran® 8100

TECHNICAL DATA

Description

Daran® 8100 is an aqueous anionic copolymer emulsion for high water vapor and oxygen barrier applications where thermoformability is needed.

Applications

- Pharma base coat
- Thermoformable substrates

Storage

Protect from the effects of weathering and light. Store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product. Contact with common metals such as mild steel copper, zinc, or aluminum should be avoided.

Features

- High barrier for WVTR and OTR performance
- High crystallinity
- Thermoformable
- Good heat seal strength
- High total solids
- Low surface tension for good wettability

General Characteristics

Appearance	Creamy white
Non-Volatile Content	60%, 110 °C, 1h (Filter Papers)
pH	3.0 neat, pH meter
Density	1.29 g/cm ³ , 25°C
Viscosity*	22 mPa sec
Surface Tension	32 dynes/cm
Alcohol Tolerant	No

*Brookfield (25 °C) LVF, Spindle #1, 60 rpm

Safety and Handling

Please refer to our safety data sheet for information relating to product safety.

Please contact your Milliken representative for further product information including chemical registrations, food contact status, and other regulatory details.

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

NORTH AMERICA Spartanburg, SC, USA Tel: 800-910-5592 Tel: 864-503-2430 millichem@milliken.com	EUROPE Gent, Belgium Tel: 32-9-265-1100 Tel: 32-9-265-1195 eurochem@milliken.com	LATIN AMERICA Sao Paulo, Brazil Tel: 55-11-3043-7942 Tel: 55-11-3043-7096 lachim@milliken.com	LATIN AMERICA Mexico City, Mexico Tel: 52-55-3088 3600 Tel: 52-55-9000 2643 lachim@milliken.com	ASIA Singapore Tel: 65-6377-0770 Tel: 65-6377-0990 asiachem@milliken.com	ASIA Shanghai Tel: 86-21 6145-5555 Tel: 86-21 6145-5558 asiachem@milliken.com	ASIA Pune, India Tel: 91.20.6730.7501 Tel: 91.20.6730.7514 asiachem@milliken.com
--	---	--	--	---	--	---