


Akustische Werte

GLASSHOUSE / Eden / Kew



Schallabsorptionsgrad (ISO 354)


Trittschallverbesserungsmaß (ISO 140-8 / ISO 10140-3)

Glasshouse WellBAC® Comfort
 α_w 0.30 Klasse D

Glasshouse WellBAC® Comfort
 ΔL_w 30dB

Alpha α_s Schallabsorptionsgrad

Frequenz (Hz)	WellBAC® Comfort α_s
100	0.00
125	0.02
160	0.03
200	0.03
250	0.05
315	0.08
400	0.19
500	0.51
630	0.36
800	0.26
1000	0.25
1250	0.25
1600	0.26
2000	0.30
2500	0.33
3150	0.36
4000	0.41
5000	0.43



α_{pi} Werte (WellBAC® Comfort)					
125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz
0.00	0.05	0.35	0.25	0.30	0.40

α_w	Klasse
(Gesamtwert)	
0.30	D