


Acoustic Values

COLOUR COMPOSITIONS VOLUME III



Sound Absorption (ISO 354)


Impact Sound (ISO 140-8 / ISO 10140-3)

Colour Compositions Volume III
Cushion α_w 0.25 Class E

Colour Compositions Volume III
Cushion ΔL_w 31dB

Sound absorption coefficient α_s

FREQUENCY (Hz)	Cushion α_s
100	0.03
125	0.01
160	0.04
200	0.02
250	0.07
315	0.09
400	0.28
500	0.59
630	0.29
800	0.21
1000	0.18
1250	0.19
1600	0.23
2000	0.26
2500	0.29
3150	0.33
4000	0.36
5000	0.40



α_p values (Cushion)

125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz
0.05	0.05	0.40	0.20	0.25	0.35

α_w Class

α_w (overall value)	Class
0.25	E