AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 **Test Number** : 20-002618 **Issue Date** : 24/06/2020

Print Date : 24/06/2020 **Order Number** : 6701207506

Sample Description Clients Ref : "Organic 18 Base (Multi-Colour/ Multi-Design)

Tufted loop pile carpet plank- Backing: WELLBAC Comfort

End Use: Flooring

Nominal Composition: 100% Nylon

Nominal Mass per Unit Area/Density: Approx: 2610g/m2

Nominal Thickness: Approx: 5mm

ASISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 25/05/2020
Date Tested 23/06/2020

CHF Value	1	2	3	Mean	
Length	7.8	7.4	7.4	7.5	kW/m²
Width	8.0	-	-	-	kW/m²
Smoke Value	1	2	3	Mean	
Length	162	185	173	173	%.min
Width	93	-	-	-	%.min

Melting Yes

206676 44412 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No. : Accreditation No.

: Accreditation No. 985 : Accreditation No. 1356

983

ess otherwise stated. AWTA nples. The above test results



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

MICHAEL A. JACKSON B.Sc.(Hons)

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Milliken (Australia) Pty Ltd

171 Briens Road Northmead NSW 2152 Test Number : 20-002618 Issue Date : 24/06/2020

Print Date : 24/06/2020 Order Number : 6701207506

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

206676 44412 Page 2 of 2

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

- Mechanical Testing

Performance & Approvals Testing

: Accreditation No.

: Accreditation No.

983 985 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

MICHAEL A. JACKSON B.Sc.(Hons)