


Valeurs acoustiques

DOWN TO EARTH / Grounded / Leaf / Twig



Absorption des bruits aériens (ISO 354)


Isolation des bruits d'impacts (ISO 140-8 / ISO 10140-3)

Down to Earth Comfort Lite® α_w 0.30 Classe D

Down to Earth Comfort Lite® ΔL_w 32dB

Coefficient d'absorption acoustique alpha α_s

Fréquence (Hz)	Comfort Lite® α_s
100	0.02
125	0.03
160	0.04
200	0.04
250	0.05
315	0.09
400	0.17
500	0.38
630	0.39
800	0.26
1000	0.23
1250	0.24
1600	0.25
2000	0.28
2500	0.30
3150	0.33
4000	0.37
5000	0.40



α_p Valeurs (Comfort Lite®)					
125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz
0.05	0.05	0.30	0.25	0.30	0.35

α_w	Classe
(valeur globale) 0.30	D