ACCS
AUSTRALIAN CARPET CLASSIFICATION SCHEME



Registration Certificate

Carpet Name:	*BK9 CUSTOM DESIGNS*
Licensee:	*MILLIKEN (AUSTRALIA) PTY LTD*
Licence Number:	*008*
Label Number:	*16098*
ACCS Contract Grading:	*CEHD 4**
ACCS Residential Grading:	*NONE*
Suitable for Stairs:	*Yes*
Date Printed:	*20/06/2016*



CARPET
IT JUST FEELS BETTER

Allan Firth
Secretary ACCS

AUSTRALIAN CARPET MARK

Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303
PO Box 7172, St Kilda Road, Melbourne Victoria 3004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560
Email: info@carpetoz.com.au • www.carpetinstitute.com.au

This certificate remains the property of the Carpet Institute of Australia Limited.

Carpet Details: **Company: MILLIKEN (AUSTRALIA) PTY LTD** **Label No: 16098**
Licence No: 008 **Office No: 6372**

Names:
BK9 CUSTOM DESIGNS

Details:

Awarded Res Grade:	NONE	
Awarded Con Grade:	CEHD	4*
Registered On:		20/06/2016
Active:		Yes
Date In-Active:		
Manufacture Method:		Tufted
Twist Set:		N/A
Dyeing Method:		Yarn Dyed
#Colours/Designs:		12
Backing Type:		Foam
Felted:		N/A
Spinning System:		BCF
Insect Resist Agent:		N/A
Filament:		/
Master Product:		14205

Hexapod Scores:

	Texture		Colour		Thickness	
		WA		WA	(mm)	(%)
1500:	4.0	3.5	4.0	4.0	0.4	16.7
8000:	3.0	2.5	3.5	3.0	0.6	25.0

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	11.9	16	16
Volume Density:	12.2	12.2	20
Tuft Density:	9	9	9
Dyn Load:	4	4	5
Stat Load:	5	5	5
Soiling Prop:	14	14	16
Abrasion Res:	7.9	7.9	10
Sub Total:	64	68.1	81
Panel Assess:	15	15	19
Total:	79	83.1	100

Calc Residential Grade: REHD2 6*
Calc Contract Grade: CHD 3*

Test Results:

Pile Mass g/m² (oz/yd²):	509	(15.0)
SPM g/m² (oz/yd²):	310	(9.1)
Stated Pile Height (mm):		2.0
Minimum Pile Height (mm):		0.0
Maximum Pile Height (mm):		0.0
Dynamic Loading Loss (%):		20.6
Static Loading Loss (%):		8.8
Tex (g/1000m):		250
Measured Pile Thickness (mm):		2.4
Machine Gauge (Tufts/dm):		47.0
Meas Tufts Perp to Selvedge:		48.1
Meas Tufts Para to Selvedge:		38.9
Treated For Soiling Resistance:		Yes
Soil Resist Inhibitor:		Yes
Stain Resist Inhibitor:		Yes

Quality Assurance Test:

Cut Pile (%):	0
Loop Pile (%):	100
Panel Assessment Contract:	15
Panel Assessment Residential:	15
Suitable For Stairs:	Yes
Tile: Yes SheetGoods:	No
Fibre Signature:	NBA:100

Calculations

Pile Height(mm):		3.4
Tuft Density(per dm²):		1871.1
GSPM(g/m²):		397.0
GSPM (abrasive) (g/m²):		275.0
Soiling Propensity:	12.0	+2.0

OAF Values

OAF: 4.2

Calc Density (+-5%):0.12 0.129 0.14
Base Fibre: NYLON

Benchmarks:

RHD1	0	RHD2	3.5
REHD1	3.5	REHD2	3.5

Environmental Classification:

ECS:
Level: 0

	Calc	B/M	P/F
Acoustic:	2.4	3	
Thermal:	18.6	15	PASS
VOC:			
TVOC	0		

Notes:

20/06/2016 - Cloned From Master - (14205) by S Murphy.